



LAFRENTZ ROAD MARKING
 A Division of Canadian Road Builders Inc.

Zone 4, 1-26228 Township Road 530A
 Acheson, AB T7X 5A7

Phone: 780 962-7800
 Fax: 780 960-1666
 Email: info@lafrentz.ca

Lafrentz System 400 Material Specifications Sheet

Viscosity:	
Daniel Flow Gauge	Between 13-14
Haake VT 02, Spindle 2	Approx. 14,000 mPa · s
Density	1.85 – 1.90 kg/l
Shore D Hardness	50 – 60
Boiling point	100 – 101 °C
Flashpoint	10 °C (closed cup)
Freezing point	-48 °C
Specific Gravity	2.0 g/ml
V.O.C.	0
Luminescence (white)	> 75%