



Lafrentz Road Marking

TEMPERATURE GUIDE FOR ADDING BPO CATALYST

Temp	Maximum BPO % by Weight	Maximum BPO Weight (based on 30 kg pail)	Pot Life
0°	2.0% – 2.5%	600g – 750g	20 minutes
10°	1.0% – 1.5%	300g – 450g	15 minutes
20°	0.5% – 1.0%	150g – 300g	10 minutes
30°	0.5%	150g	10 minutes